

# **Appendices**

# Appendix I

## A Brief Chronology

NOTE: Texts are date of first publication. Instruments and processes are approximate date of first commercial introduction unless otherwise noted.

METALLURGY	INORGANIC ANALYTICAL CHEMISTRY
14th century BC—Reduction of iron ore	14th century BC—Babylonians use fire assay to test the purity of gold
700 BC—Iron displaces bronze	
14th Century AD—Blast furnace for pig iron	
1530— <i>De la Pirotechnia</i> (Vannocio Biringuccio)	
1556— <i>De re Metallica</i> (Georg Agricola)	
	1574— <i>Beschreibung allerfurnemisten mineralischen Ertzt und Bergwercksarten</i> (Lazarus Ercker)
1600—Wrought iron, cementation process for steel	
1613—Reverberatory furnace	
	1661— <i>The Sceptical Chymist</i> (Robert Boyle)
	1681—Phlogiston theory
1709—precoking for ironmaking	
1722— <i>On the Art of Converting Iron to Steel</i> (R. A. F. de Réaumur)	
	1729—Bouguer's Law
1734— <i>Treatise on Copper</i> (E. Swedenborg)	
1742—Crucible process for steel	
	1768—Lambert's Law
	1774—Joseph Priestley discovers oxygen
1780—Role of carbon in steelmaking discovered	
1784—Puddling process for wrought iron	
1808—Widmanstätten structure discovered in meteorites	1808— <i>New System of Chemical Philosophy</i> (John Dalton)
	1811—Avogadro's Theory
	1828—Berzelius: table of atomic weights
	1832—Gay-Lussac titrates silver with chloride
1836—Hot dip galvanizing	
1856—Bessemer (Kelley) process	1856— <i>Lehrbuch der chemisch-analytischen Titrimethode</i> (K. F. Mohr)
	1859—Beer's law
	1862—First issue: <i>Zeitschrift für Analytische Chemie</i> (Fresenius)
1863—Sorby: microscopic metallography	
	1871—Mendeleev: periodic table
	1877—synthetic acid/base indicators
1882—Hadfield steel (high manganese)	
1886—Hall/Heroult electrolytic process for aluminum	
	1887—Arrhenius equation
1888—Open hearth (Siemens) process; thermocouple (Le Chatelier)	

## 232 CHEMICAL ANALYSIS OF METALS

METALLURGY	INORGANIC ANALYTICAL CHEMISTRY
1889—Nickel steels	1889—Nerst equation
	1894— <i>Die wissenschaftlichen Grundlagen der analytischen Chemie</i> (W. Ostwald)
1898—Tempered high-tungsten tool steel	
1899—Electric arc furnace	
1900—Silicon-iron	
	1903—Conductivity titrations
1904—Vanadium steels	
1905—Monel alloys	
1906—Age hardening of aluminum alloys discovered	
	1909—Sorensen: pH concept
1910—Direct reduction of iron ore (Hoganas process)	
1913—Stainless steel	1913—Moseley: X-ray spectra of the elements
	1914— <i>Rapid Methods for the Chemical Analysis of Special Steels</i> . . . (C. M. Johnson)
1915—Nickel-iron high-permeability alloys	
	1920—Glass pH electrodes
1922—Galvannealing process	
	1923—Fluorescent indicators; Debye-Hückel theory; Brønsted theory
	1925—Redox indicators
1926—Type 310 stainless steel	
1927—High-frequency induction furnace; cobalt-iron high-saturation alloys	
1928—Type 304 stainless steel	
	1929— <i>Applied Inorganic Analysis</i> , 1st ed. (Hillebrand, Lundell, and Hoffman)
1931—Alnico magnet alloys	1931— <i>Chemical Analysis of Iron and Steel</i> (Lundell, Hoffman, and Bright)
1932—Cobalt-base alloys (vitallium)	
1933—High-strength low-alloy steels	
	1934—Ion exchange resins
1935—Electroslag remelting process (developed)	
	1938—Coulometric titrations; <i>Outlines of Methods of Chemical Analysis</i> (Lundell and Hoffman)
	1940—UV/visible spectrophotometer; <i>Fire Assaying</i> (Shepherd and Dietrich)
	1942—Direct reading spectrophotometer
1943—Precipitation-hardening austenitic stainless steel	
	1944–46—Analytical chemistry of the Manhattan Project (published, 1950)
1945—Vacuum arc remelting furnace	
1949—Sintered aluminum powder	
1950—Type 201 stainless steel; Sendzimer mill	1950—Direct-reading optical emission spectrometer
1951—Titanium alloys	
1952—Basic oxygen process (L-D)	
	1953— <i>Applied Inorganic Analysis</i> , 2nd ed. (Hillebrand, Lundell, Bright, and Hoffman)
	1955—X-ray fluorescence spectrometer
1960—Rapid solidification processing; maraging steel; vacuum degassing	1960—Flame atomic absorption spectrophotometer
1962—Basic oxygen process (Stora-Kaldo)	
1963—Continuous casting	

METALLURGY	INORGANIC ANALYTICAL CHEMISTRY
	1964—Ion selective electrodes
	1965—d-c plasma emission spectrometer
	1968—Grimm glow discharge lamp
1970—Electroslag remelting widely used; argon-oxygen decarburization (AOD); rare earth-cobalt magnet alloys	1970—Graphite furnace atomic absorption spectrophotometer
1975—Amorphous metals	1975—ICP emission spectrometer
1978—Metal-matrix composites	
	1979—Dual-beam diode array spectrophotometer
1980—Large-scale ladle refining	1980—Total reflection X-ray fluorescence spectrometer
1982—Single crystal alloys	
	1983—Glow discharge mass spectrometer; single-beam diode array spectrophotometer
1984—Neodymium-iron-boron magnet alloy	1984—ICP-mass spectrometer
1985—Ductile-ordered alloys (intermetallic compounds)	1985—Glow discharge atomic absorption spectrophotometer (solids sampling)
1987—Ion implantation; beam processing; metallurgy of surfaces	1987—Laser ablation-ICP-MS
	1989—Early robot labs for steel control
	1990—Echelle-CID optical emission spectrometer
1992— <i>Nano-Structured Materials</i> (journal) begins publication	1992—ICP-OES-MS system

## REFERENCES

- Beck II, C. M., *Analytical Chemistry*, Vol. 66, No. 4, 1994, pp. 224A–239A.
- Beckman, A. O., Gallaway, W. S., Kaye, W., and Ulrich, W. F., *Analytical Chemistry*, Vol. 49, No. 3, pp. 280A–300A.
- Cohen, M., *Advancing Materials Research*, P. A. Psaras and H. D. Langford, Eds., National Academy Press, Washington, DC, 1987, pp. 51–110.
- Day, R. A. and Underwood, A. L., *Quantitative Analysis*, 2nd ed., Prentice-Hall, Englewood Cliffs, New Jersey, 1967.
- Jarnutowski, R., Ferraro, J. R., and Lankin, D. C., *Spectroscopy*, Vol. 7, No. 7, 1992, pp. 22–35.
- Johansson, A., *Analytica Chimica Acta*, Vol. 206, 1988, pp. 97–107.
- Kallmann, S., *Analytical Chemistry*, Vol. 56, No. 9, 1984, pp. 1020A–1028A.
- Kranzberg, M. and Smith, C. S., *Materials Science and Engineering*, Vol. 37, No. 1, 1977, pp. 1–37.
- Morrall, F. R., *Wire and Wire Products*, Vol. 1, No. 1, 1971, pp. 52–76.
- Smith, C. S., *The Sorby Centennial Symposium on the History of Metallurgy*, Gordon and Breach, New York, 1965.
- Wadhams, A. J., *Metals and Alloys*, September 1931, pp. 166–175.

# Appendix II

## The Chemical Behavior of Analytes

**NOTE:** Element name and symbol are followed by atomic number, atomic weight, and common aqueous oxidation states with the most stable state underlined. Abbreviations—(s): solution; (p): precipitate; (o): organic; (a): aqueous; RT: room temperature.

<b>Element</b>	Aluminum (Al) 13 26.982 <u>+3</u>	Antimony (Sb) 51 121.757 <u>+3</u> , +5, -3	Arsenic (As) 33 74.922 <u>+3</u> , +5, -3
Useful precipitations	NaOH: (s) NH <sub>4</sub> OH: (p) 8-hydroxyquinoline: (p)	Acid sulfide: (p) Basic sulfide:(s) Accompanies Fe + NH <sub>4</sub> OH: (p)	Acid sulfide: (p) Basic sulfide: (s) Accompanies Fe + NH <sub>4</sub> OH: (p)
Useful solvent extractions	Ethyl ether/ HCl— from Mo, Fe: (a); 8-hydroxyquinoline-CHCl <sub>3</sub> /pH 9: (o)	Ethyl acetate/1.5 M HCl—Sb(V): (o) TOPO/ MIBK: (o)	
Useful volatilizations/ distillations		SbH <sub>3</sub> (gas at RT) SbCl <sub>3</sub> (b.p. approx. 200°C)	AsH <sub>3</sub> (gas at RT) AsCl <sub>3</sub> (b.p. 108°C)
Other useful separations/ comments	Amphoteric Mercury cathode: (a)		Highly toxic
Best methods at high concentrations	Volum.: Titr. with standard acid after AlF <sub>3</sub> precip. at pH 10 Grav.: 8-hydroxyquinoline	Volum.: Titr. with BrO <sub>3</sub> <sup>-</sup> Grav.: as Sb <sub>2</sub> S <sub>3</sub>	Volum.: Titr. with BrO <sub>3</sub> <sup>-</sup> Grav.: as As metal
Best methods at low concentrations	FAA: 309.3 nm ICP-OES: 369.1 nm (Intf.: Mo) Color: 8-hydroxyquinoline	FAA/GFAA: 217.6 nm ICP-OES: 206.8 nm (Intf.: Cr) Color: Brilliant Green; Rhodamine B	FAA/GFAA: 193.7 nm ICP-OES: 193.7 nm (Intf.: Al) Color: AsH <sub>3</sub> + pyridine + Ag- diethyldithiocarbamate; arsenomolybdate

<b>Element</b>	Barium (Ba) 56 137.327 <u>+2</u>	Beryllium (Be) 4 9.0122 <u>+2</u>	Bismuth (Bi) 83 208.980 <u>+3</u> , (+5)
Useful Precipitations	Sulfate: (p) Chromate: (p)—from Sr Ammonium phosphate (ammoniacal): (p)	NaOH: (s) NH <sub>4</sub> OH: (p)	Acid sulfide: (p) Basic sulfide: (p)
Useful Solvent Extractions			Dithizone - CHCl <sub>3</sub> : (o) TOPO-MIBK: (o)
Useful Volatilizations/ Distillations			
Other Useful Separations/ Comments	Yellow-green flame test Mercury cathode: (a)	Highly toxic Mercury cathode: (a)	
Best Methods at High Concentrations	Volum.: EDTA (ind.: Eriochrome Black T) Grav.: as the sulfate	Grav.: as BeO after NH <sub>4</sub> OH precip.; Photoneutron emission	Grav.: as BiOCl or BiPO <sub>4</sub>
Best Methods at Low Concentrations	FAA: 553.6 nm ICP-OES: 493.4 nm	FAA: 234.9 nm ICP-OES:313.0 nm Color: Aluminon; Fluorimetric: quinalizarin; morin	FAA/GFAA: 223.1 nm (pk. ht. best) ICP-OES: 223.0 nm (Intf.: Cu, Ni) Color: dithizone

<b>Element</b>	Boron (B) 5 10.811 +3	Cadmium (Cd) 48 112.411 +2	Calcium (Ca) 20 40.078 +2
Useful precipitations		Acid sulfide: (p) Basic sulfide: (p) NaOH: (p) NH <sub>4</sub> OH: (s)	Oxalate: (p)—from Mg Chromate: (s)—from Ba
Useful solvent extractions	CHCl <sub>3</sub> —BF <sub>3</sub> : (o) (tetraphenyl arsonium chloride; methylene blue)		
Useful volatilizations/ distillations	B(OCH <sub>3</sub> ) <sub>3</sub> (b.p. 68.7°C) BF <sub>3</sub> (b.p. -99°C) BCl <sub>3</sub> (b.p. 12.4°C)		
Other useful separations/ comments	Mercury cathode: (a) Ion exchange (remove other cations and anions) Borates: yellow-green flame test	Highly toxic	Mercury cathode: (a) Yellow-red flame test
Best methods at high concentrations	Volum.: Mannitol complex— titr. released H <sup>+</sup> with standard NaOH. ICP-OES: 249.6 nm (Intf.: Co)	Grav.: as Cd <sub>2</sub> P <sub>2</sub> O <sub>7</sub> ; as Cd metal (electrolytic) ICP-OES: 226.5 nm	Volum.: EDTA (ind.: Eriochrome Black T) Grav.: as CaC <sub>2</sub> O <sub>4</sub>
Best methods at low concentrations	ICP-OES: 249.6 nm (Intf.: Co) Color: curcumin (after methyl borate distillation); dianthrimide (direct)	FAA/GFAA: 228.8 nm ICP-OES: 226.5 nm Color: dithizone	FAA: 422.7 nm ICP-OES: 317.9 nm (Intf.: Cr)

<b>Element</b>	Chromium (Cr) 24 51.996 +2, +3, +6	Cobalt (Co) 27 58.933 +2, +3	Copper (Cu) 29 63.546 +1, +2
Useful precipitations	NaOH: Cr(III)(p), Cr(VI)(s) NH <sub>4</sub> OH: Cr(III)(p); Cr(VI)(s) Na <sub>2</sub> O <sub>2</sub> fusion /H <sub>2</sub> O leach: (s) Ag <sup>+</sup> , Hg <sub>2</sub> <sup>2+</sup> , Ba <sup>2+</sup> , Pb <sup>2+</sup> : (p)— Cr(VI)	ZnO: (s)—from Fe; NaOH:(p) NH <sub>4</sub> OH:(s), but Fe and Al coprecip.	Acid sulfide: (p) Basic sulfide: (p) (NH <sub>4</sub> ) <sub>2</sub> S: (p) NaOH:(p) NH <sub>4</sub> OH: (s)
Useful solvent extractions		Tetraphenylarsonium chloride- CHCl <sub>3</sub> : (o)	Neocuproine-CHCl <sub>3</sub> : Cu(I):(o)
Useful volatilizations/ distillations	CrO <sub>2</sub> Cl <sub>2</sub> (b.p. 117°C)		
Other useful separations/ comments	Mercury cathode is slow to remove Cr (VI)	Ion Exchange (Cl <sup>-</sup> ) from Ni, Cu, Fe; Co <sup>2+</sup> : pink/ Co <sup>3+</sup> : blue	Ion exchange(Cl <sup>-</sup> )— from Ni, Co, Fe
Best methods at high concentrations	Volum.: oxidize with persulfate, titr. with ferrous ammonium sulfate	Volum.: oxidize with excess K <sub>2</sub> Fe(CN) <sub>6</sub> , back titr. with Co <sup>2+</sup> Grav.: electroplate as metal	Grav.: electrolytic as metal Volum.: iodometric
Best methods at low concentrations	FAA: 357.9 nm ICP-OES: 267.7 nm Color: diphenylcarbazine	FAA: 240.7 (D <sub>2</sub> arc); 242.5 (Zeeman) ICP-OES: 228.6 nm (2nd order) Color: nitroso-R salt, tetraphenyl arsonium chloride	FAA: 324.8 nm ICP-OES: 324.7 nm Color: diethyldithiocarbamate; neocuproine

**236 CHEMICAL ANALYSIS OF METALS**

<b>Element</b>	Gallium (Ga) 31 69.723 +3	Germanium (Ge) 32 72.61 +4	Gold (Au) 79 196.967 +3
Useful precipitations	NH <sub>4</sub> OH: (p) NaOH: (s) Cupferron: (p) 8-hydroxyquinoline: (p)	Acid sulfide: (p) Basic sulfide: (s)	NaNO <sub>2</sub> : (p), as metal from the Pt group Acid sulfide: (p) Basic sulfide: (p)
Useful solvent extractions	Ethyl ether/HCl: Ga(o); Al(a)		Isopropyl ether/dil. HBr: (o) Ethyl ether/HCl: (o)
Useful volatilizations/ distillations		GeCl <sub>4</sub> (b.p. 83.1°C)	
Other useful separations/ comments	Metal melts at 29.75°C, boils at 1980°C (widest liquid range)	Highly toxic	Gold salts are strong oxidizing agents (Au <sup>3+</sup> + 3e <sup>-</sup> → Au <sup>0</sup> )
Best methods at high concentrations	Grav.: as Ga <sub>2</sub> O <sub>3</sub> , after precip. with NH <sub>4</sub> OH	Grav.: acid sulfide precip., diss. in NH <sub>4</sub> OH, oxidize with H <sub>2</sub> O <sub>2</sub> , ignite to GeO <sub>2</sub>	Fire assay Grav.: as metal. after reduction with oxalic acid, SO <sub>2</sub> , NaNO <sub>2</sub> , or hypophosphorous acid
Best methods at low concentrations	FAA: 287.4 nm ICP-OES: 294.4 nm Color: 8-hydroxyquinoline-CHCl <sub>3</sub>	FAA: 265.1 nm ICP-OES: 209.4 nm Color: phenylfluorone	FAA: 242.8 nm ICP-OES: 242.8 nm

<b>Element</b>	Hafnium (Hf) 72 178.49 +4	Indium (In) 49 114.818 +3	Iridium (Ir) 77 192.22 +3, +4, +6
Useful precipitations	NaOH: (p); NH <sub>4</sub> OH: (p); p-Bromomandelic acid: (p); Cupferron: (p); (NH <sub>4</sub> ) <sub>2</sub> HPO <sub>4</sub> : (p) In all cases Zr accompanies.	NaOH: (p) NH <sub>4</sub> OH: (p) Dilute (pH 2-3) acid sulfide: (p) Ammonium oxalate (pH 8): (p)	Acid sulfide: (p) Basic sulfide: (s)
Useful solvent extractions	TOPO-Cyclohexane/HNO <sub>3</sub> : (o) Zr accompanies.	Ethyl ether/HCl: (o)	Ethyl ether/HCl: (o)
Useful volatilizations/ distillations			
Other useful separations/ comments	Mercury cathode: (a) Hf and Zr can be separated by ion exchange		IrCl <sub>4</sub> : dark brown
Best methods at high concentrations	Grav.: as HfO <sub>2</sub> after cupferron precip. and ignition; as HfP <sub>2</sub> O <sub>7</sub> after (NH <sub>4</sub> ) <sub>2</sub> HPO <sub>4</sub> precip. and ignition (do not overwash).	Grav.: as In <sub>2</sub> O <sub>3</sub> after precip. with NH <sub>4</sub> OH Volum.: Titr. with K <sub>2</sub> Fe(CN) <sub>6</sub>	Grav.: as metal after precip. with 2-mercaptobenzothiazole followed by reduction in H <sub>2</sub>
Best methods at low concentrations	ICP-OES: 273.8 nm (Intf.: Fe, Mo) Color: Pyrocatechol Violet; Xylenol Orange	FAA: 325.6 nm ICP-OES: 451.1 nm Color: dithizone	ICP-OES: 224.3 nm

<b>Element</b>	Iron (Fe) 26 55.847 +2, +3	Lead (Pb) 82 207.2 +2, +4	Magnesium (Mg) 12 24.305 +2
Useful precipitations	NH <sub>4</sub> OH: (p) NaOH: (p) Cupferron (as Fe <sup>3+</sup> ): (p)	Acid sulfide: (p) Basic sulfide: (p) Sulfate: (p) Chromate: (p)	(NH <sub>4</sub> ) <sub>2</sub> HPO <sub>4</sub> : (p) NaOH: (p) 8-Hydroxyquinoline (ammoniacal sol.): (p)
Useful solvent extractions	Cupferron-CHCl <sub>3</sub> /10% HCl: (o) Ethyl ether/HCl: (o) Acetylacetone-CHCl <sub>3</sub> (as Fe <sup>3+</sup> at pH 1): (o)	Dithizone-CHCl <sub>3</sub> : (o) TOPO-MIBK: (o)	8-Hydroxyquinoline-CHCl <sub>3</sub> / pH 10: (o)
Useful volatilizations/ distillations			
Other useful separations/ comments	Ion exchange (Cl <sup>-</sup> system)— from Ni, Co, Cu	Highly toxic	Mercury cathode: (a)
Best methods at high concentrations	Volum.: Reduce with SnCl <sub>2</sub> , then titr. with K <sub>2</sub> Cr <sub>2</sub> O <sub>4</sub> or Ce (IV)	Grav.: as PbSO <sub>4</sub> ; Electrolytic (as PbO)	Volum.: EDTA (ind.: Eriochrome Black T) Grav.: as Mg <sub>2</sub> P <sub>2</sub> O <sub>7</sub> after precip. with (NH <sub>4</sub> ) <sub>2</sub> HPO <sub>4</sub> and ignition.
Best methods at low concentrations	FAA: 248.3 nm ICP-OES: 259.9 nm Color: o-phenanthroline; thiocyanate; 2, 2'-bipyridyl	FAA: 283.3 nm ICP-OES: 220.3 nm (Intf.: Co, Ni, Al) Color: dithizone	FAA: 285.2 nm ICP-OES: 279.0 nm (Intf.: Mn, Cr, Fe)

<b>Element</b>	Manganese (Mn) 25 54.938 +2, +3, +4, +6, +7	Mercury (Hg) 80 200.59 +1, +2	Molybdenum (Mo) 42 95.94 +3, +5, +6
Useful precipitations	Acid sulfide: (s) Basic sulfide: (p) (NH <sub>4</sub> ) <sub>2</sub> HPO <sub>4</sub> : (p) NaOH: (p)	Acid sulfide: (p) (insol. HNO <sub>3</sub> ) Basic sulfide: (p)	NH <sub>4</sub> OH: (s) NaOH: (s) Acid sulfide: (p) Basic sulfide: (s) $\alpha$ -Benzoinoxime:(p)
Useful solvent extractions			Ethyl ether/HCl: (o)
Useful volatilizations/ distillations		Hg <sup>0</sup> (b.p. 356.58°C) HgCl <sub>2</sub> (b.p. 302°C)	MoO <sub>3</sub> (loss begins at approx. 600°C)
Other useful separations/ comments		Highly toxic Liquid at R.T. Forms amalgams with many metals	Cl <sup>-</sup> /F <sup>-</sup> System anion exchange—from W, Ti, Nb, Ta, etc.
Best methods at high conc.	Volum.: oxidize with persulfate, titr. with arsenite (visual or potentiometric) Volum.: complex with pyrophosphate, titr. with KMnO <sub>4</sub> (potentiometric)	Volum.: Titr. with thiocyanate (Fe <sup>3+</sup> ind.) Grav.: as HgS after precip. with (NH <sub>4</sub> ) <sub>2</sub> S from basic sol.	Grav.: as MoO <sub>3</sub> after precip with $\alpha$ -Benzoinoxime and ignition Volum.: Pass through Jones reductor, collect in excess std. ferrous ammonium sulfate, titr. excess with KMnO <sub>4</sub>
Best methods at low concentrations	Color: meta-periodate (as MnO <sub>4</sub> <sup>-</sup> ) FAA: 279.5 nm ICP-OES: 257.6 nm	Cold vapor AA/ FAA/GFAA: 253.7 nm ICP-OES: 435.8 nm	FAA: 313.3 nm ICP-OES: 202.0 nm Color: thiocyanate; toluene-3,4- dithiol



<b>Element</b>	Nickel (Ni) 28 58.693 +2	Niobium (Nb) 41 92.906 (+3), +5	Osmium (Os) 76 190.23 +4, +6, +8
Useful precipitations	Dimethylglyoxime: (p) NaOH: (p) NH <sub>4</sub> OH: (s) Basic sulfide: (p)— after removal of acid sulfide group	NaOH: (p) NH <sub>4</sub> OH: (p) Cupferron: (p)	Acid sulfide: (p) Basic sulfide: (p)
Useful solvent extractions	Dimethylglyoxime-CHCl <sub>3</sub> : (o)		
Useful volatilizations/ distillations			OsO <sub>4</sub> (b.p. 130°C)
Other useful separations/ comments	Ion Exchange (Cl <sup>-</sup> system)— from Fe, Co, Cu	Mercury cathode: (a) Ion exchange (Cl <sup>-</sup> /F <sup>-</sup> system)— from Mo, Ti, W, Ta, etc.	OsCl <sub>4</sub> : yellow Highly toxic, especially as oxide vapor
Best methods at high concentrations	Grav.: as dimethylglyoximate Volum.: excess EDTA, back titr. with Bi(NO <sub>3</sub> ) <sub>3</sub>	Grav.: as Nb <sub>2</sub> O <sub>5</sub> , after precip. with cupferron and ignition	Grav.: as the metal after distillation of OsO <sub>4</sub> and reduction in H <sub>2</sub>
Best methods at low concentrations	FAA: 232.0 nm ICP-OES: 231.6 nm (Intf.: Co) Color: Ni-dimethylglyoxime complex (in presence of I <sub>2</sub> )	Color: H <sub>2</sub> O <sub>2</sub> in conc. H <sub>2</sub> SO <sub>4</sub> ; hydroquinone in conc. H <sub>2</sub> SO <sub>4</sub> ICP-OES: 309.4 nm (Intf.: V)	Color: thiourea; ephedrine-HCl ICP-OES: 225.6 nm

<b>Element</b>	Palladium (Pd) 46 106.42 +2, +4	Phosphorus (P) 15 30.974 +3, +5, -3	Platinum (Pt) 78 195.08 +2, +4
Useful precipitations	Dimethylglyoxime: (p)—from weak acid sol. Cupferron: (p)	NaOH: (s) NaOH + Na <sub>2</sub> O <sub>2</sub> : (s) Accompanies Fe + NH <sub>4</sub> OH: (p)	Acid sulfide: (p) Basic sulfide: (s)
Useful solvent extractions	Pd-dimethylglyoximate—CHCl <sub>3</sub> : (o)	Phosphomolybdate complex— N-butanol: [ox.—yellow: (o); reduced—blue: (a)]	
Useful volatilizations/ distillations		PCl <sub>3</sub> (b.p. 76.1°C)	
Other useful separations/ comments	PdI <sub>2</sub> : black precipitate (soluble in NH <sub>4</sub> OH + iodide)	Highly toxic volatile compounds Ion exchange (alumina column)	Pt <sup>o</sup> appears as a red colloid if reduced with SnCl <sub>2</sub> , or as a black precip. if reduced with formaldehyde in basic sol.
Best methods at high concentrations	Grav.: as Pd- dimethylglyoximate from weak acid sol.	Grav.: as Mg <sub>2</sub> P <sub>2</sub> O <sub>7</sub> after precip. with MgCl <sub>2</sub> + NH <sub>4</sub> OH Volum.: Precip. as ammonium phosphomolybdate, add excess std. NaOH and backtitr. with std. HCl	Grav.: as Pt metal after acid sulfide precip. and ignition to the metal Fire Assay
Best methods at low concentrations	ICP-OES: 229.7 nm FAA: 247.6 nm Color: α-furfuraldoxime; bromide after extraction of phenylthiourea complex	Color: phosphomolybdate; phosphomolybdovanadate ICP-OES: 214.9 nm (Intf.: Cu)	ICP-OES: 214.4 nm FAA: 265.9 nm Color: p - nitrosodimethylaniline

Element	Rhenium (Re) 75 186.207 <u>+4, +6, +7</u>	Rhodium (Rh) 45 102.906 <u>+3, +4</u>	Ruthenium (Ru) 44 101.07 <u>+3, +4, +6, +8</u>
Useful precipitations	Nitron: (p) Tetraphenylarsonium chloride: (p) $\alpha$ -Benzoinoxime: (s)— from Mo	Acid sulfide: (p) Basic sulfide: (p)	Acid sulfide: (p) Basic sulfide: (p) Bismuthiol: [Ru(III)] (p)
Useful solvent extractions	Ethyl ether/HCl: (o)		
Useful volatilizations/ distillations	Re <sub>2</sub> O <sub>7</sub> (b.p. 362°C)— from Mo		RuO <sub>4</sub> (decomp. 108°C) RuOF (b.p. 184°C)
Other useful separations/ comments	Ion exchange—from Mo Yields yellow-brown precip. with HCl + SnCl <sub>2</sub> + KCNS	RhCl <sub>3</sub> : red Yields yellow color with thiocyanate	Highly toxic volatile compounds RuCl <sub>3</sub> : dark brown
Best methods at high concentrations	Grav.: as tetraphenylarsonium perrhenate; as nitron perrhenate ICP-OES: 197.3 nm	Grav.: as Rh metal after precip. as the acid sulfide and reduction in H <sub>2</sub> ICP-OES: 233.5 nm	Grav.: as Ru metal after precip. as the acid sulfide and reduction in H <sub>2</sub> ICP-OES: 240.3 nm
Best methods at low concentrations	ICP-OES: 197.3 nm	ICP-OES: 233.5 nm FAA: 343.5 nm Color: sodium hypochlorite	ICP-OES: 240.3 nm FAA: 349.9 nm Color: p- nitrosodimethylalanine; rubeanic acid

Element	Selenium (Se) 34 78.96 <u>+4, +6, -2</u>	Silicon (Si) 14 28.086 <u>+4</u>	Silver (Ag) 47 107.868 <u>+1</u>
Useful precipitations	Hydrazine sulfate: as the element (p) Accompanies Fe + NH <sub>4</sub> OH: (p)	Fuming with HClO <sub>4</sub> or H <sub>2</sub> SO <sub>4</sub> : as silicic acid (p)	NaOH: (p) NH <sub>4</sub> OH: (s) Chloride: (p) Acid sulfide: (p) Basic sulfide: (p)
Useful solvent extractions		Silicomolybdate-N-butanol: [ox.: yellow(o); red.: blue (a)]	
Useful volatilizations/ distillations	SeOCl <sub>2</sub> (b.p. 175.5°C) H <sub>2</sub> Se (gas at R.T.)	SiF <sub>4</sub> (gas at R.T.) H <sub>2</sub> SiF <sub>6</sub> (b.p. 300°C)	
Other useful separations/ comments	Highly toxic	Carries down B as it precipitates as SiO <sub>2</sub>	Pb <sup>2+</sup> , Hg <sub>2</sub> <sup>2+</sup> , Tl <sup>+</sup> , Bi <sup>3+</sup> , Sb <sup>3+</sup> may contaminate AgCl
Best methods at high concentrations	Grav.: as the element, reduced by H <sub>2</sub> SO <sub>3</sub> , SnCl <sub>2</sub> , or hydroxylamine-HCl	Grav.: as SiO <sub>2</sub> after dehydration with HClO <sub>4</sub> and/ or H <sub>2</sub> SO <sub>4</sub>	Fire Assay Volum.: titr. with thiocyanate Grav.: as AgCl (protect from light); as metal— electroplate out of oxalate or persulfate sol.
Best methods at low concentrations	ICP-OES: 196.0 nm (Intf.: Al, Co, Fe, Mn, Mg) FAA/GFAA: 196.0 nm Color: 3, 3'-diaminobenzidine	Color: silicomolybdate FAA: 251.6 nm ICP-OES: 251.6 nm	FAA/GFAA: 328.1 nm ICP-OES: 328.1 nm

## 240 CHEMICAL ANALYSIS OF METALS

Element	Strontium (Sr) 38 87.62 +2	Sulfur (S) 16 32.066 +4, +6, -2	Tantalum (Ta) 73 180.948 +5
Useful precipitations	Oxalate: (p)—from Ba and Mg NaOH fusion/H <sub>2</sub> O leach: (p) Sulfate: (p)	BaCl <sub>2</sub> : as BaSO <sub>4</sub> : (p)	Cupferron: (p) NH <sub>4</sub> OH: (p) NaOH: (p) Hydrolysis with H <sub>2</sub> SO <sub>3</sub> after fuming with HClO <sub>4</sub> : as hydrous Ta <sub>2</sub> O <sub>5</sub> : (p)
Useful solvent extractions			
Useful volatilizations/distillations		H <sub>2</sub> S (gas at R.T.)	
Other useful separations/comments	Mercury cathode: (a) Scarlet red flame test	H <sub>2</sub> S is highly toxic Ion exchange (alumina column)	F <sup>-</sup> /Cl <sup>-</sup> system anion exchange No color with H <sub>2</sub> O <sub>2</sub> (unlike Nb in H <sub>2</sub> SO <sub>4</sub> and Ti in dilute acid)
Best methods at high concentrations	ICP-OES: 407.8 nm Grav.: as oxalate	Grav.: as BaSO <sub>4</sub> — first oxidize S with Br <sub>2</sub> —reduce Fe before adding BaCl <sub>2</sub> Volum.: Ignite in O <sub>2</sub> to SO <sub>2</sub> , titr. iodimetrically	Grav.: as Ta <sub>2</sub> O <sub>5</sub> after ion exchange separation, cupferron precipitation and ignition
Best methods at low concentrations	FAA: 407.8 nm ICP-OES: 407.8 nm	IR abs: ignite to SO <sub>2</sub> Color: pararosaniline (after ignition to SO <sub>2</sub> )	Color: pyrogallol ICP-OES: 240.0 nm (Intf.: Co, Fe)

Element	Tellurium (Te) 52 127.60 +4, +6, -2	Thallium (Tl) 81 204.383 +1, +3	Thorium (Th) 90 232.038 +4
Useful precipitations	Hydrazine sulfate or sodium hypophosphite: as the element (p) Accompanies Fe + NH <sub>4</sub> OH: (p) Acid sulfide: (p) Basic sulfide: (s)	Chromate: as Tl <sub>2</sub> CrO <sub>4</sub> : (p); Iodide: as TlI (p); Chloride: as TlCl (p); Weak acid sulfide: (p); Basic sulfide: (p)	NH <sub>4</sub> OH: (p) NaOH: (p) Fluoride: (p) Oxalate (pH 3-4): (p) Iodate: (p) (NH <sub>4</sub> ) <sub>2</sub> HPO <sub>4</sub> : (p)
Useful solvent extractions	TOPO-MIBK: (o)	Ethyl ether/ HCl: (o) TOPO-MIBK: (o)	Cupferron-butyl acetate/ 0.5M H <sub>2</sub> SO <sub>4</sub> : (o)
Useful volatilizations/distillations	TeCl <sub>2</sub> (b.p. 328°C) H <sub>2</sub> Te (gas at R.T.)		
Other useful separations/comments	Highly toxic; Se can be distilled away from Te (HCl/H <sub>2</sub> SO <sub>4</sub> )	Highly toxic; Imparts emerald-green color to colorless flame; Fluoresces in NaCl under short λ UV	Highly toxic; H <sub>2</sub> O <sub>2</sub> : (p) in HNO <sub>3</sub> medium
Best methods at high concentrations	Volum.: titr. with K <sub>2</sub> Cr <sub>2</sub> O <sub>7</sub> (diphenylamine ind.) Grav.: as the element (H <sub>2</sub> SO <sub>3</sub> + hydrazine · HCl reduction)	Grav.: as Tl <sub>2</sub> CrO <sub>4</sub> from NH <sub>4</sub> OH sol. Volum.: Titr. with Ce(IV) ICP-OES: 190.9 nm	Grav.: as ThO <sub>2</sub> after precip. with oxalic acid ICP-OES: 283.7 nm
Best methods at low concentrations	FAA/GFAA: 214.3 nm ICP-OES: 214.3 nm Color: iodine complex	FAA/GFAA: 276.8 nm ICP-OES: 190.9 nm	ICP-OES: 283.7 nm

Element	Tin (Sn) 50 118.710 +2, +4	Titanium (Ti) 22 47.88 +3, +4	Tungsten (W) 74 183.84 (+3), +6
Useful precipitations	Acid sulfide: (p) Basic sulfide: (s) NH <sub>4</sub> OH: (p) NaOH: (s) Cupferron: (p)	NH <sub>4</sub> OH: (p) NaOH: (p) Cupferron: (p) Na <sub>2</sub> CO <sub>3</sub> fusion/ H <sub>2</sub> O leach: (p)	NaOH: (s) NH <sub>4</sub> OH: (s) Basic sulfide: (s) $\alpha$ -Benzoinoxime (coprecip. with excess Mo only): (p)
Useful solvent extractions	TOPO-MIBK: (o)		
Useful volatilizations/ distillations	SnCl <sub>4</sub> (b.p. 114.1°C) SnI <sub>4</sub> (b.p. 364.5°C)		
Other useful separations/ comments	May be electrodeposited from acid oxalate sol.	Ti(III): violet Ti(IV): colorless Phosphate is insoluble	Cinchonine aids precip. of WO <sub>3</sub> by dilute acid hydrolysis
Best methods at high concentrations	Volum.: Titr. with I <sub>2</sub> after reduction with metallic Pb, Ni, Al, or Zn Grav.: as SnO <sub>2</sub> from HNO <sub>3</sub>	Grav.: as TiO <sub>2</sub> after ion exchange, NaOH sep. from W, cupferron precip. and ignition Volum.: Jones reductor into excess std. ferric sulfate; back-titr. with KMnO <sub>4</sub>	Grav.: as WO <sub>3</sub> after ion exchange and precip. with cinchonine (diss. in NaOH and weigh impurities)
Best methods at low concentrations	FAA/GFAA: 286.3 nm ICP-OES: 189.9 nm Color: phenylfluorone	FAA: 364.3 nm ICP-OES: 334.9 nm Color: H <sub>2</sub> O <sub>2</sub> in dil. H <sub>2</sub> SO <sub>4</sub> ; diantipyrilmethane; hydroquinone in conc. H <sub>2</sub> SO <sub>4</sub>	ICP-OES: 207.9 nm (Intf. Al) Color: hydroquinone in conc. H <sub>2</sub> SO <sub>4</sub> ; toluene-3,4-dithiol; thiocyanate

Element	Uranium (U) 92 238.029 +4, +6	Vanadium (V) 23 50.942 +3, +4, +5	Zinc (Zn) 30 65.39 +2	Zirconium (Zr) 40 91.224 +4
Useful precipitations	NaOH: (p); NH <sub>4</sub> OH: (p)— must be V & CO <sub>2</sub> -free; Cupferron: (p); (NH <sub>4</sub> ) <sub>2</sub> CO <sub>3</sub> : (s) —from Fe, Al & Cr which precip.	Na <sub>2</sub> O <sub>2</sub> + NaOH: (s) Cupferron: (p); Accompanies Fe + NH <sub>4</sub> OH: (p) NH <sub>4</sub> OH: (s) NaOH: (s)	NH <sub>4</sub> OH: (s) NaOH: (s) Acid sulfide: (s) Basic sulfide: (p) (NH <sub>4</sub> ) <sub>2</sub> HPO <sub>4</sub> : (p)	NaOH: (p) NH <sub>4</sub> OH: (p) Cupferron: (p) p-Bromomandelic acid: (p) (NH <sub>4</sub> ) <sub>2</sub> HPO <sub>4</sub> : (p) In all cases Hf accompanies
Useful solvent extractions	Ethyl ether/HNO <sub>3</sub> : UO <sub>2</sub> <sup>2+</sup> — (o)		Dithizone-CHCl <sub>3</sub>	TOPO-Cyclohexane/ HNO <sub>3</sub> : (o) Hf accompanies
Useful volatilizations/ distillations				
Other useful separations/comments	Highly toxic U(VI): yellow U(IV): green Forms soluble complex with CO <sub>3</sub> <sup>2-</sup>	Mercury cathode: (a) III: V <sup>3+</sup> (blue); IV: V <sub>2</sub> O <sub>4</sub> <sup>2+</sup> (blue); VO <sup>2+</sup> (blue); V: VO <sub>2</sub> <sup>+</sup> (yellow); VO <sub>3</sub> <sup>-</sup> (orange)	Amphoteric Whitish flame test	Mercury cathode: (a) Zr and Hf can be separated by ion exchange
Best methods at high concentrations	Grav.: as U <sub>3</sub> O <sub>8</sub> after NH <sub>4</sub> OH precip. and ignition Volum.: Titr. with KMnO <sub>4</sub>	Volum.: Oxidize with boiling HNO <sub>3</sub> , titr. potentiometrically with ferrous ammonium sulfate	Grav.: as Zn <sub>2</sub> P <sub>2</sub> O <sub>7</sub> after precip. with (NH <sub>4</sub> ) <sub>2</sub> HPO <sub>4</sub> and ignition Volum.: Potentiometric titr. with K <sub>2</sub> Fe(CN) <sub>6</sub>	Grav.: as ZrO <sub>2</sub> after cupferron precip. and ignition; as ZrP <sub>2</sub> O <sub>7</sub> after (NH <sub>4</sub> ) <sub>2</sub> HPO <sub>4</sub> precip. and ignition (do not overwash)
Best methods at low concentrations	ICP-OES: 386.0 nm Fluorimetry: of fused NaF + sample with UV (<300 nm) excitation	FAA: 318.4 nm ICP-OES: 292.4 nm (Intf.: Mo) Color: H <sub>2</sub> O <sub>2</sub> (unlike the Ti complex, not bleached by HF)	FAA: 213.9 nm ICP-OES: 213.9 nm (Intf.: Ni, Cu) Color: dithizone Fluorimetry: benzoin complex	ICP-OES: 339.1 nm Color: Pyrocatechol Violet; Xylenol Orange

# Appendix IIA

## The Alkali Metals

*NOTE:* The only stable aqueous oxidation state is +1. All can be separated by ion exchange/ ion chromatography. Francium has no stable isotopes.

Element	Useful Precipitations	Useful Solvent Extractions	Flame Test	Flame Emission/ ICP Wavelength	FAA Wavelength	Other Methods
Lithium (Li) 3 6.941			Crimson	460.3 nm	670.8 nm	Fluorimetry: 8-Hydroxy-quinoline
Sodium (Na) 11 22.990	Zinc uranyl acetate: (p)		Yellow	330.2 nm (Many intf.)	589.0 nm	
Potassium (K) 19 39.098	ClO <sub>4</sub> <sup>-</sup> : (p) IO <sub>4</sub> <sup>-</sup> : (p) PtCl <sub>6</sub> <sup>2-</sup> : (p) Tetraphenylborate: (p)	18 - Crown - 6 Ether	Rose/violet	766.5 nm	766.5 nm	X-ray fluorescence: K $\alpha_1$ = 3.7412 Å
Rubidium (Rb) 37 85.468	ClO <sub>4</sub> <sup>-</sup> : (p) Tetraphenylborate: (p)	18 - Crown - 6 Ether	Rose/violet	420.2 nm	780.0 nm	X-ray fluorescence K $\alpha_1$ = 0.9255 Å
Cesium (Cs) 55 132.905	ClO <sub>4</sub> <sup>-</sup> : (p) Tartrate: (p) Tetraphenylborate: (p)	21 - Crown - 7 Ether	Red/violet	452.7 nm	852.1 nm	X-ray fluorescence K $\alpha_1$ = 0.4003 Å

# Appendix IIB

## The Rare Earths

**NOTE:** This category includes the lanthanides and chemically similar elements. All form precipitates with HF, ammonium oxalate,  $\text{NH}_4\text{OH}$ ,  $\text{NaOH}$ , and  $\text{Na}_2\text{CO}_3/\text{H}_2\text{O}$  leach. All are left in the aqueous solution on the mercury cathode. All can be separated by ion exchange. All can be determined by X-ray fluorescence. Promethium has been excluded since it has no stable isotopes.

Element	Comments	ICP Wavelength	FAA Wavelength	Other Methods
Scandium (Sc) 21 44.956 +3	Forms complexes more readily than the lanthanides	361.4 nm		
Yttrium (Y) 39 88.906 +3	Properties are half-way between Sc and La	371.0 nm	410.2 nm	
Lanthanum (La) 57 138.906 +3	$\text{I}_2 + \text{La}(\text{OH})_3$ ; blue color (no other rare earth exhibits this effect)	398.8 nm		
Cerium (Ce) 58 140.115 +3, +4	$\text{Ce}^{3+}$ : colorless $\text{Ce}^{4+}$ : orange-red	418.6 nm (Intf.: Zr)		Volum.: oxidize with persulfate, titr. with ferrous ammonium sulfate (potentiometric)
Praseodymium (Pr) 59 140.908 +3	$\text{Pr}^{3+}$ : green	390.8 nm		
Neodymium (Nd) 60 144.24 +3	$\text{Nd}^{3+}$ : pale violet	401.2 nm		
Samarium (Sm) 62 150.36 (+2), +3	$\text{Sm}^{2+}$ : red (decomposes in $\text{H}_2\text{O}$ ) $\text{Sm}^{3+}$ : yellow	359.3 nm	429.7 nm	
Europium (Eu) 63 151.965 +2, +3	$\text{Eu}^{2+}$ : colorless $\text{Eu}^{3+}$ : pale pink	382.0 nm	459.4 nm	Volum.: Jones reductor into excess std. ferric sulfate; back-titr. with $\text{K}_2\text{Cr}_2\text{O}_7$ (Sm and Y not reduced and do not interfere)
Gadolinium (Gd) 64 157.25 +3	$\text{Gd}^{3+}$ : colorless	342.2 nm		
Terbium (Tb) 65 158.925 +3	$\text{Tb}^{3+}$ : pale pink	350.9 nm		
Dysprosium (Dy) 66 162.50 +3	$\text{Dy}^{3+}$ : yellow	353.2 nm	421.2 nm	

## 244 CHEMICAL ANALYSIS OF METALS

Element	Comments	ICP Wavelength	FAA Wavelength	Other Methods
Holmium (Ho) 67 164.930 +3	Ho <sup>3+</sup> : yellow	345.6 nm		
Erbium (Er) 68 167.26 +3	Er <sup>3+</sup> : pale violet	326.5 nm	400.8 nm	
Thulium (Tm) 69 168.934 +3	Tm <sup>3+</sup> : green	313.1 nm	371.8 nm	
Ytterbium (Yb) 70 173.04 (+2), +3	Yb <sup>2+</sup> : only with applied potential (-1.5V) Yb <sup>3+</sup> : yellow	328.9 nm	398.8 nm	
Lutetium (Lu) 71 174.967 +3	Lu <sup>3+</sup> : colorless	261.5 nm		